



# FUD-3576, Revision: A SM-GDF-8/125 Optical Fiber

You have selected an application designed fiber, not fully released which may have a longer lead time than our standard products.

Parameter	Min	Nom	Max	Unit	Compliance
Operating Wavelength	1060		1600	nm	Design
Cladding Attenuation at 1095nm	0		15	dB/km	Measured
Core NA	0.1		0.11		Design
Cladding NA (5%)	0.46				Design
Cutoff	940		1060	nm	Measured
Mode Field Diameter at 1060 nm	7.6	8.6	9.6	μm	Measured
Core Diameter	8		9	μm	Measured
Clad Diameter	124		126	μm	Measured
Core/Clad Offset	0		1	μm	Measured
Coating Diameter	230		260	μm	Measured
Proof test Level	100		120	kpsi	Measured
Comments	Coating Requirements: Low Index Coating Other Requirements: Round Fiber				



7 Airport Park Road, East Granby, CT 06026 • 860.408.5000 • Toll-free 866.466.0214 • Fax 860.844.0210 • E-mail [info@nufern.com](mailto:info@nufern.com) • [www.nufern.com](http://www.nufern.com) •  
Nufern products are manufactured under an ISO 9001:2008 certified quality management system.



Custom developed fiber (FUD) specifications are subject to change without notice. Other configurations such as alternative form factors, optimized cut-off and UV cured color coating may be available. Let us know how Nufern can assist with your requirements.