



FUD-3600, Revision: C PS-GDF-8/130 Optical Fiber

You have selected an application designed fiber, not fully released which may have a longer lead time than our standard products.

Parameter	Min	Nom	Max	Unit	Compliance
Operating Wavelength	1060		1600	nm	Design
Core Attenuation at 1200 nm	0		15	dB/km	Measured
Core Attenuation at 1300 nm	0		20	dB/km	Measured
Cladding Attenuation at 1095nm	0		15	dB/km	Measured
Core NA		0.095			Design
Second Clad NA (5%)	0.46				Design
Cutoff	920	960	1000	nm	Measured
Mode Field Diameter at 1060 nm	8	8.5	9	μm	Measured
Core Diameter		8.4		μm	Design
Clad Diameter	129		131	μm	Measured
Core/Clad Offset	0		0.5	μm	Measured
Coating Diameter	230	245	260	μm	Measured
Proof test Level	100		120	kpsi	Measured
Comments	Photosensitivity Requirements: Photosensitive fiber. Coating Requirements: Low index polymer coating.				



7 Airport Park Road, East Granby, CT 06026 • 860.408.5000 • Toll-free 866.466.0214 • Fax 860.844.0210 • E-mail info@nufern.com • www.nufern.com •
 Nufern products are manufactured under an ISO 9001:2008 certified quality management system.



Custom developed fiber (FUD) specifications are subject to change without notice. Other configurations such as alternative form factors, optimized cut-off and UV cured color coating may be available. Let us know how Nufern can assist with your requirements.

NS048 - 06/17/2015