



FUD-3793, Revision: C MM-GDF-25/400-11FA Optical Fiber

You have selected an application designed fiber, not fully released which may have a longer lead time than our standard products.

Parameter	Min	Nom	Max	Unit	Compliance
Operating Wavelength	800		2000	nm	Design
Cladding Attenuation at 1095nm	0		15	dB/km	Measured
Core NA	0.1		0.12		Design
Cladding NA (5%)	0.46				Design
Core Diameter	22.5		27.5	μm	Measured
Clad Diameter	385		415	μm	Measured
Core/Clad Offset	0		2	μm	Measured
Coating Diameter	530		570	μm	Measured
Proof test Level	100		120	kpsi	Measured
Comments	Other Requirements: Round fiber with low index polymer coating.				



7 Airport Park Road, East Granby, CT 06026 • 860.408.5000 • Toll-free 866.466.0214 • Fax 860.844.0210 • E-mail info@nufern.com • www.nufern.com •
Nufern products are manufactured under an ISO 9001:2008 certified quality management system.

Custom developed fiber (FUD) specifications are subject to change without notice. Other configurations such as alternative form factors, optimized cut-off and UV cured color coating may be available. Let us know how Nufern can assist with your requirements.

