



# FUD-4329, Revision: A LMA-YDF-10/125-HI Optical Fiber

You have selected an application designed fiber, not fully released which may have a longer lead time than our standard products.

Parameter	Min	Nom	Max	Unit	Compliance
Operating Wavelength	1030		1130	nm	Design
Cladding Attenuation at 1095nm	0		15	dB/km	Measured
Peak Cladding Absorption at 915 nm	1.3		1.8	dB/m	Measured
Core NA	0.07		0.08		Measured
Cladding NA (5%)	0.46				Design
Core Diameter	10		12	μm	Measured
Clad Diameter (Flat-to-Flat)	123		127	μm	Measured
Core/Clad Offset	0		1	μm	Measured
Coating Diameter	230		260	μm	Measured
Proof test Level	100		120	kpsi	Measured
Comments	Coating Requirements: Low Index polymer coating.				



7 Airport Park Road, East Granby, CT 06026 • 860.408.5000 • Toll-free 866.466.0214 • Fax 860.844.0210 • E-mail [info@nufern.com](mailto:info@nufern.com) • [www.nufern.com](http://www.nufern.com) • Nufern products are manufactured under an ISO 9001:2008 certified quality management system.



Custom developed fiber (FUD) specifications are subject to change without notice. Other configurations such as alternative form factors, optimized cut-off and UV cured color coating may be available. Let us know how Nufern can assist with your requirements.

NS193 - 06/30/2015