

10/125 Erbium/Ytterbium-Doped Multimode Double Clad Fiber



Coherent's proprietary rare earth doping technology is used to deliver Er/Yb co-doped fibers with industry leading performance and reliability. These fibers feature 10 micron diameter core and a 125 micron diameter cladding with a 0.21 NA. The fiber design has been finely optimized to deliver the best performances for two distinct configurations. MM-EYDF-10/125-XP is designed to deliver ultra-high efficiencies while ensuring low threshold and high gain factors, ideal for CATV and telecom amplifiers. On the other hand, MM-EYDF-10/125-XPH is optimized to achieve tens of Watts of output power with high efficiency and suppressed 1 μ m parasitic ASE, offering unmatched stability. The large core of the fiber allows for shorter fiber lengths in amplifier and laser systems to reduce the impact of non-linear effects. Utilizing Coherent's proprietary NuCOAT-FA coating technology, these fibers offer the best damp and dry heat performance available and ensure extended operating lifetime.

Typical Applications

- Laser and amplifiers at 1.5 μ m (CATV and Telecom)
- Military and commercial LIDAR
- High peak power, pulsed fiber amplifiers

Features & Benefits

- Optimized XP design — High efficiency and low parasitic 1 μ m ASE
- Large core — Enables shorter fiber length for high-power pulsed amplifiers
- Double clad design — High power performance and high power conversion efficiency
- NuCOAT-FA fluoroacrylate coating — Greater fiber durability in extreme operating and storage conditions
- All fiber proof tested to > 100 kpsi — Critical for ensuring long term reliability when coiling

Optical Specifications

	MM-EYDF-10/125-XP	MM-EYDF-10/125-XPH
Operating Wavelength	1530 – 1625 nm	1530 – 1625 nm
Core NA	0.210	0.210
First Cladding NA (5%)	≥ 0.46	≥ 0.46
Cladding Attenuation	≤ 30.0 dB/km @ 1095 nm	≤ 30.0 dB/km @ 1095 nm
Cladding Absorption	2.90 ± 0.60 dB/m at 915 nm	2.90 ± 0.60 dB/m at 915 nm
Core Absorption	50.0 ± 20.0 dB/m near 1530 nm	100.0 ± 20.0 dB/m near 1530 nm

Geometrical & Mechanical Specifications

	MM-EYDF-10/125-XP	MM-EYDF-10/125-XPH
Cladding Diameter (flat-to-flat)	125.0 ± 2.0 μ m	125.0 ± 2.0 μ m
Core Diameter	10.0 ± 1.0 μ m	10.0 ± 1.0 μ m
Coating Diameter	215.0 ± 5.0 μ m	215.0 ± 5.0 μ m
Coating Concentricity	< 5.0 μ m	< 5.0 μ m
Core/Clad Offset	≤ 1.00 μ m	≤ 1.00 μ m
Coating Material	Low Index Acrylate	Low Index Acrylate
Operating Temperature Range	N/A	-40 to 85 $^{\circ}$ C
Proof test Level	≥ 100 kpsi (0.7 GN/m ²)	≥ 100 kpsi (0.7 GN/m ²)



Nufern • 7 Airport Park Road, East Granby, CT 06026 • 860.408.5000 • Toll-free 866.466.0214 • Fax 860.844.0210 • Email: tech.sales@coherent.com
www.coherent.com ; www.shop.coherent.com • Coherent products are manufactured under an ISO 9001:2008 certified quality management system.



Custom developed fiber (FUD) specifications are subject to change without notice. Other configurations such as alternative form factors, optimized cut-off and UV cured color coating may be available. Let us know how Coherent can assist with your requirements.