# 105 & 106.5 Micron Core Power Delivery Fibers



Coherent's specialty multimode step-index fibers are designed for compatibility with the majority of fiber-coupled, single-emitter, diode-laser packages and support the diode laser power delivery market. These power delivery fibers are available in a 105/125 core/clad ratio in low and high NA versions and also in a 106.5/125 core/clad ratio with high NA. The 106.5/125 fiber features high temperature acrylate as a standard coating in order to meet the challenges of harsh environments and high pump powers demanded by today's need for robust applications. Other fiber diameters and coatings are available upon request.

### **Typical Applications**

- Fiber coupled diode lasers
- · Couplers and pump combiners

#### **Features & Benefits**

MM-S105/125-12A

• 0.12, 0.15 and 0.22 NA — Compatible with majority of fiber-coupled, diode-laser packages

MM-S105/125-15A

- Exceptional geometric uniformity and core/clad concentricity Ease of coupling to pump diodes
- Pure Silica Core High resistance to optical damage

# **Optical Specifications**

Operating Wavelength Core NA OH Level

## Geometrical & Mechanical Specifications

Cladding Diameter
Core Diameter
Coating Diameter
Core/Clad Offset
Coating Material
Operating Temperature Range
Short Term Bend Radius
Long Term Bend Radius
Prooftest Level

800 – 1600 nm	800 — 1600 nm	800 — 1600 nm	800 — 1600 nm	
$0.120 \pm 0.020$	$0.150 \pm 0.020$	$0.220 \pm 0.020$	$0.220 \pm 0.020$	
Low	Low	Low	Low	
125.0 ± 2.0 μm	125.0 ± 2.0 μm	125.0 ± 2.0 μm	125.0 ± 1.0 μm	
$105.0 \pm 3.0 \ \mu m$	$105.0 \pm 3.0  \mu m$	$105.0 \pm 3.0  \mu m$	$106.5 \pm 1.5 \mu m$	
24E 0 . 1E 0	245.0 . 15.0	245.0 . 15.0	245 0 . 15 0	

MM-S105/125-22A

MM-S106.5/125-22HTA

 $245.0 \pm 15.0 \, \mu m$  $245.0 \pm 15.0 \,\mu m$  $245.0 \pm 15.0 \, \mu m$  $245.0 \pm 15.0 \, \mu \text{m}$ ≤ 3.00 µm  $\leq 3.00 \, \mu m$  $\leq 3.00 \, \mu m$  $\leq 3.00 \, \mu m$ Acrylate Acrylate Acrylate High Temperature Acrylate -55 to 125 °C -40 to 85 °C -40 to 85 °C -40 to 85 °C ≥ 12 mm ≥ 12 mm ≥ 12 mm ≥ 12 mm ≥ 25 mm ≥ 25 mm ≥ 25 mm ≥ 25 mm  $\geq$  100 kpsi (0.7 GN/m<sup>2</sup>)  $\geq$  100 kpsi (0.7 GN/m<sup>2</sup>) ≥ 100 kpsi (0.7 GN/m²) ≥ 100 kpsi (0.7 GN/m²)



